



HIGH PERFORMANCE VpCI™ COATINGS

VpCI-378



PRODUCT DESCRIPTION

VpCI-378 is a water-based concentrate designed as a complete replacement for oil-based corrosion preventives. VpCI-378 forms a brown emulsion in water and is applied to metal surfaces by spraying or dipping. The wide dilution range with water allows flexibility to customize the length of protection required vs. applied cost. The protective coating is also translucent and in ambient conditions becomes dry-to-touch 30 minutes from application. VpCI-378 is designed to be removed with Cortec® VpCI-414 or other conventional alkaline cleaners.

VpCI-378 is designed to protect ferrous and non-ferrous metals in sheltered areas, indoors or in packaging, with no direct exposure to rain or outdoor elements. In many operations, removal is not necessary since coatings or paints can be applied directly over treated surfaces at dilutions over 1:15.

FEATURES

- Forms clear and dry film, which renders attractive appearance to protected parts
- Heat stable
- Displaces water from metal surfaces
- Easy to remove if necessary
- Eliminates cleaning and housekeeping problems associated with oils
- Superior protection and complete replacement for rust-inhibiting oils
- Emulsifiable, thus environmentally acceptable and safe to apply
- Unique vapor phase action protects uncoated and difficult-to-reach areas
- Economical - can be diluted up to 1 part VpCI-378 to 20 parts water
- User friendly
- Lubricating properties

METALS PROTECTED

- Carbon steel
- Stainless steel
- Cast iron
- Aluminum
- Copper and alloys

TYPICAL APPLICATIONS

- Castings, forgings, tubular parts, machined and honed metal components
- Gears, pumps, electric motors, housings, textile and printing equipment
- Precision machined parts, structural steel, sintered metals, bars and roll stock
- Additive to parts washers and rinse water systems, hydroblasting and hydrotesting
- Use as a quenching fluid or in dipping applications operating at elevated temperatures

PRODUCT PREPARATION

Add VpCI-378 to water as follows:

Short-term protection (1-6 months):

1 part concentrate to 10-20 parts water

Medium-term protection (6-12 months):

1 part concentrate to 6-10 parts water

Long-term protection (up to 2 years):

1 part concentrate to 1-5 parts water

TYPICAL PROPERTIES

Appearance	Brown viscous liquid
Corrosion Resistance	Up to 24 months
Drying Time	30-60 minutes
Film Type	Dry, clear
Flash Point	>200°F (>93°C), TCC
Odor	Mild
pH	9.8-10.7 (Neat)
Density	8.1-8.3 lb/gal (0.97-0.99 kg/l)

PACKAGING AND STORAGE

VpCI-378 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes and bulk. The product should be stored sealed in a heated warehouse to avoid freezing. VpCI-378 has a shelf life of 24 months.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:



www.esvasolutions.com

printed on recycled paper



10% post consumer

Revised 4/6/06. Cortec Corporation 1998-2006. All rights reserved. Supersedes: 10/6/00.

© 1998-2006, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.