



VpCI®-144

Environmentally Friendly Moisture Barrier Paper, Powered by Nano-VpCI®, Patented (US 5,894,040)



PRODUCT DESCRIPTION

EcoShield VpCI-144 is the premium moisture barrier corrosion inhibiting paper in the industry. Our patented Vapor phase Corrosion Inhibiting technology has revolutionized the way metals are protected in an enclosed package. EcoShield VpCI-144 paper provides superior corrosion protection for both ferrous and non-ferrous metals, which eliminates the need to inventory a variety of papers for all the different types of metal you need to protect. This product also shows excellent oil and grease resistance.

Our EcoShield VpCI-144 paper is coated with a water-based barrier coating. Historically, polyethylene and wax coatings have been used to seal porous paper to provide a moisture barrier and/or moisture-vapor barrier. When coated this way the resulting paper product is an environmental problem and cannot be recycled through normal channels. EcoShield VpCI-144 paper provides an environmentally friendly alternative to polyethylene and wax paper, with water vapor barrier properties that are comparable to polyethylene coated paper.

EcoShield VpCI-144 is environmentally safe, non-toxic, and fully recyclable/repulpable. That means EcoShield VpCI-144 can be recycled into other types of paper products such as boxes, cardboard, and other corrugated materials. It also means that EcoShield VpCI-144 can be "repulped": made into or mixed with pulp to make new paper products.

EcoShield VpCI-144 paper is made from the highest quality recycled neutral natural kraft paper: our paper is made without the use of any chlorine or other bleaching chemicals. This eliminates package contamination found with other competing VCI/VPI papers. Parts protected with EcoShield VpCI-144 can be painted, welded, and soldered. The thin protective film doesn't influence physical properties of most sensitive electrical and electronic components, including conductivity and resistivity.

TYPICAL APPLICATIONS

EcoShield VpCI-144 paper can be used to protect products for storage and shipment in a wide variety of ways: end closures for shipping tubes, insert strips for recessed areas in large packages, and as sheet liners or separators between products.

The typical applications are:

- Metal production: coils, wire reels, plate, bar, etc.
- Metal forging and die casting: raw and machined forgings and castings
- Metalworking: stamping, sheet metal work, springs, bearings, fasteners, tube, pipe, jewelry, silverware, etc.
- Finished products: engines, machinery, equipment, tools, hardware, appliances, instruments, motors, etc.
- Electrical and electronic: components, controls, printed circuit boards, etc.

FEATURES

- Combines corrosion protection, moisture barrier properties, oil and grease resistivity into one step
- Fully repulpable according to Fibre Box Association Voluntary Standard
- Contains no nitrites, phosphates, silicones, chromates, other heavy metals, or toxic products
- Natural grade paper eliminates package contamination
- One product protects against corrosion of ferrous and non-ferrous metals
- Conforms to military specifications MIL-P-3420E
- Conforms to NACE Standards TM0208-2008 and RP0487-2000
- Protective film does not need to be removed prior to further surface finishing or coating application



METHOD OF APPLICATION

Products should be packaged as soon after cleaning as possible. Keep the EcoShield VpCl paper as close to the surface of the product as practical, leaving no barrier between the EcoShield VpCl paper and the metal surface to be protected.

Use approximately 1 square foot (0.09 m²) of EcoShield VpCl paper for every 3 square feet (0.28 m²) of surface to be protected; and 1 square foot (0.09 m²) of VpCl paper for every 0.5 cubic foot (0.01 m³) of void space. For long-term storage of up to ten years, enclose the wrapped product in an airtight package.

Standard construction of VpCl-144: Neutral natural paper coated on one side with the blend of water-barrier coating and VpCl material and with the barrier coating on the reverse side.

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
- Cast Iron
- Aluminum Alloys
- Copper
- Brass (≤30% Zn)
- Solder

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY SEALED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

TYPICAL PROPERTIES

Property	TAPPI Method	Unit	Cortec
Basis Weight	T-410	lbs/3000 ft ² (g/m ²)	54.8 (89.2)
Caliper (thickness)	T-411	mils (micrometers)	5 (125)
Tear-MD	T-414	g	47.5
Tear-CD	T-414	g	58.5
Dry Tensile-CD	T-494	lbs/in (kg/mm)	17.68 (0.315)
Dry Tensile-MD	T-494	lbs/in (kg/mm)	47.14 (0.8418)
TEA-CD	T-494	ft-lbs/ft (J/m ²)	3.6 (38.8)
TEA-MD	T-494	ft-lbs/ft (J/m ²)	1.9 (20.5)
Stretch-CD	T-404	%	4.26
Stretch-MD	T-404	%	1.47
Ink floa	T-530	seconds	15
Smooth-nonprint	T-538	sheffield	240
Smooth-VCI	T-538	sheffield	231
Internal Bond	T-541	ft-lbs/in (J/cm)	0.165 (0.064)
Abrasion-nonprint	T-476	g loss/100 rev	0.007
Abrasion-VCI	T-476	g loss/100 rev	0.002

CD=Cross Direction

MD=Machine Direction

WATER VAPOR BARRIER PROPERTIES

	VpCl-144	Polycoated Paper	Waxed Paper
WVTR** (g/hour•m ²)	0.61-0.69	0.47-0.71	6.5-6.9

PACKAGING AND STORAGE

Standard sizes: Converter rolls 48" x 26,000 feet (1.22 m x 7,925 m), roll stock 36" x 200 yards (0.91 m x 183 m), and 48" x 200 yards (1.22 m x 183 m). Custom sizes also available up to 100" (2.5 m) wide.

** Tested according to ASTM E-96, 73°F, 50%RH, Example test ranges for VpCl-144, a comparable polyethylene coated paper, and commercial wax paper.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



www.esvasolutions.com

printed on recycled paper



100% post consumer

Revised: 2/20/15. ©Cortec Corporation 2014-2015. All rights reserved. Supersedes: 3/20/14.

Cortec® is a trademark of Cortec Corporation ©- 2015, Cortec Corporation. All Rights Reserved.

Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.