

APPLICATION INSTRUCTIONS

Shrink Wrapping

1. Measure unit and determine amount of film needed, allowing at least 12" overlap at all seams.
2. Lay out film in desired preparation area, making sure it is clean and dry.
3. Place vehicle or equipment on film.
4. Pad off any sharp edges and corners.
5. Wrap or shroud equipment with film.
6. Use shrink tape to attach loose ends onto film/equipment.
7. Carefully apply heat and shrink film to desired fit.

Shrink Tunnel

VpCI-126 Shrink film can be used in shrink tunnel applications; however, the optimum temperature, speed and dwell time will vary depending on equipment and must be determined with testing.

Recommended starting point settings

Temperature range: 350-380° F (177 – 193 °C)

Speed: Low

Dwell time: 20-30 seconds

*Note: May require two passes through tunnel to achieve desired fit.

TYPICAL MECHANICAL PROPERTIES OF VpCI-126 SHRINK FILM

Property		Test Method	Units	VpCI-126 Shrink
Caliper		ASTM D6988	mil	6.00
Breaking Factor	MD	ASTM D882-02	lbs/in	14.06
	TD			14.89
Tensile Strength at Break	MD	ASTM D882-02	psi	2181.55
	TD			2363.45
Elongation at Break	MD	ASTM D882-02	%	451.38
	TD			615.18
Yield Strength	MD	ASTM D882-02	psi	1434.65
	CD			1443.89
Tear Strength	MD	ASTM D1922-06a	mN	6560.93
	CD			9700.13
Dart Drop Impact Resistance		ASTM D1709-04, Test Method A	grams	623.92

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:



printed on recycled paper  100% post consumer

Revised: 10/15/14. ©Cortec Corporation 2001-2014. All rights reserved. Supersedes: 5/9/14.

Cortec®, VpCI®-126 and Color of Blue® are registered trademarks of Cortec Corporation.

© 2014, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.

www.esvasolutions.com